



KÖSTER Crisin 76 Cream

Ficha Técnica / Número do Artigo M 278

Editado: AM-12-17

- Official test report, MFPA, Leipzig according to WTA Technical Leaflet 4-4-03, Moisture Content 95%

Solvent free resin / silane injection cream against rising damp

Características

KÖSTER Crisin Cream is a solvent free resin / silane injection cream against capillary rising moisture.

Dados Técnicos

Material basis	Resin silane combination
Color	White
Density	0,85 g / cm ³
Solids content	approx. 85 %
Consistency	pasty, firm
Application temperature	+ 5 °C to + 35 °C

Campos de aplicação

KÖSTER Crisin Cream is a retroactive DPC (Damp Proof Course) waterproofing against capillary rising moisture. It can be applied from inside and/or from the outside of the building. It can be applied in cases of high degrees of moisture penetration (95% +/- 5% saturation) and with all degrees of salt contamination.

Aplicação

Holes with a diameter of 14 mm are drilled horizontally, ideally in the lowest masonry joint. Drill until 3 cm away from the wall end, do not drill completely through the wall. The drilled holes are cleaned by flushing with water or with compressed air. The holes are spaced 10 cm apart independent of the wall thickness. KÖSTER Crisin Cream is injected from the cartridge with the proper KÖSTER Hand Pistol fitted with an injection tube. The holes can be sealed immediately with KÖSTER KB Fix 5 flush with the wall. When using self-priming processing equipment the 10 l buckets are used to refill the cartridge.

Consumo

12 cm wall thickness: approx. 110 ml / m; 36 cm wall thickness: approx. 350 ml / m

Wall thickness (cm)	Consumption (ml / m)	Yield / 310 ml cartridge (m)	Yield / 530 ml cartridge (m)
12	ca. 140	2.2	3.8
24	ca. 330	0.9	1.6
36	ca. 510	0.6	1.0

Limpeza

Clean tools immediately after use with water.

Embalagem

M 278 006	6 x 310 ml box
M 278 010	10 l balde
M 278 012	12 x 310 ml caixa
M 278 310	310 ml cartucho

Armazenamento

Store at room temperature, (approx. + 20 °C). In originally sealed packages the material can be stored for a minimum of 12 months.

Produtos relacionados

KÖSTER KB-FIX 5	Número do artigo C 515 015
KÖSTER Polysil TG 500	Número do artigo M 111
KÖSTER Restoration Plaster 1 Grey	Número do artigo M 661 025
KÖSTER Restoration Plaster 2 White	Número do artigo M 662 025
KÖSTER Restoration Plaster 2 Fast	Número do artigo M 663 030
KÖSTER Restoration Plaster 2 Light	Número do artigo M 664 025
KÖSTER Restoration Plaster 2 Light and Fast	Número do artigo M 665 025
KÖSTER Restoration Plaster E Grey	Número do artigo M 668

As informações contidas nesta ficha técnica baseia-se nos resultados da nossa pesquisa e na nossa experiência prática em campo. Todos os dados dos ensaios mencionados são valores médios que foram obtidos sob condições previamente definidas. A aplicação adequada e, logo eficaz e bem sucedida dos nossos produtos não está sujeita ao nosso controle. O instalador é responsável pela correcta aplicação tendo em consideração as condições específicas do local de construção e os resultados finais do processo de construção. Isto pode requerer ajustes às recomendações aqui mencionadas para casos normais. As especificações feitas pelos nossos colaboradores ou representantes que excedam as especificações contidas nesta ficha técnica requerem confirmação por escrito. As normas válidas para ensaios e aplicação/ instalação, orientações técnicas e regras reconhecidas da tecnologia têm que ser respeitadas em todos os momentos. A garantia poderá e será apenas aplicada à qualidade dos nossos produtos dentro do âmbito dos nossos termos e condições e na sua aplicação eficaz, adequada e bem sucedida. Esta diretriz foi tecnicamente revista; todas as versões anteriores são inválidas.